

---

## BASE OIL PURABASE 5

---

### PHYSICAL AND CHEMICAL PROPERTIES:

PROPERTY	UNIT	VALUE	TEST METHOD
Specific gravity at 15 °C	kg/m <sup>3</sup>	853	DIN 51757 / ASTM D-1298
Color	-	L 0,5	DIN ISO 2049 / ASTM D-1500
Kinematic viscosity at 40 °C	mm <sup>2</sup> /s	28,50	DIN 51562-1 / ASTM D-445
Kinematic viscosity at 100 °C	mm <sup>2</sup> /s	5,25	DIN 51562-1 / ASTM D-445
Viscosity index	-	>125	DIN ISO 2909 / ASTM D-2270
Pour point	°C	-9	DIN ISO 3016 / ASTM D-97
Flash point (COC)	°C	>230	DIN ISO 2592 / ASTM D-92
Sulfur content	mg/kg	< 5	DIN EN ISO 8754 / ASTM D-4294
Vapour loss (Noack) at 250 °C	wt.-%	< 8	DIN 51581 / ASTM D-5800
Saturates	%	> 96	ASTM D2007

**PACKAGE: BULK**