

## BASE OIL PURECUT 220LN

### PHYSICAL AND CHEMICAL PROPERTIES :

PROPERTY	UNIT	TYPICAL DATA	TEST METHOD
Density at 15 °C	kg/m <sup>3</sup>	852	DIN 51757 ASTM D-1298
Colour	-	1,0	DIN ISO 2049 ASTM D-1500
Kinematic viscosity at 40 °C	mm <sup>2</sup> /s	46,0	DIN 51562-1 ASTM D-445
Kinematic viscosity at 100 °C	mm <sup>2</sup> /s	7,40	DIN 51562-1 ASTM D-445
Viscosity index	-	118	DIN ISO 2909 ASTM D-2270
Flash point (COC)	°C	250	DIN ISO 2592 ASTM D-92
Pour point	°C	-9	DIN ISO 3016 ASTM D-97
Sulphur content	mg/kg	< 10	DIN ES ISO 8754 ASTM D-4294
Volatility (Noack test at 250 °C)	% (of weight)	3,5	DIN 51581 ASTM D-5800

**PACKAGES: BULK**

**NARMAK TRADE S.R.O.**

sídlo: Smetanova 2083/2a, Český Těšín, PSČ 737 01, DIČ: CZ04493184,  
společnost zapsaná v obchodním rejstříku vedeném Krajským soudem v Ostravě, oddíl C, vložka 63833